

Sika AnchorFix® S

Universal anchoring adhesive

Product Description

Styrenated polyester based two part anchoring adhesive.

Uses

As a fast curing anchoring adhesive for all grades of:

- Rebars / reinforcing steel
- Threaded rods
- Bolts and special fastening systems
- Concrete
- Hollow and solid masonry

Prior to any application, the suitability of the Sika AnchorFix® Adhesive for the substrate in terms of the desired bond strength, and for the prevention of surface staining or discolouration, must be confirmed by testing in a sample area. This is due to the wide variation of possible substrates, particularly in terms of strength, composition and porosity:

- Hard natural stone
- Solid rock

Characteristics / Advantages

- Fast curing
- Non-sag, even overhead
- Low wastage

Tests

Approval / Standards

Approvals for Injection systems for use in concrete :



European Technical Approval Guideline ETAG 001 -1 & 5

Bonded injection type anchor made of galvanized steel or stainless steel for non-cracked concrete: Sizes M8, M10, M12, M16, M20 and M24

EC Cert. 1020-CPD-090-029814

ETA-13 / 0721

Construction



Product Data

Colours	Part A:	white
	Part B:	black
	Part A+B mixed:	light grey

Packaging	300 ml standard cartridge, 12 per box. Pallet: 60 boxes with 12 cartridges, 720 pieces.
	380 ml coaxial cartridge, 12 per box. Pallet: 60 boxes with 12 cartridges, 720 pieces.




Storage

Storage Conditions / Shelf-Life	12 months from date of production if stored properly in original unopened, sealed and undamaged packaging in cool and dry conditions at temperatures between 0°C and +20°C. Protect from direct sunlight. All Sika AnchorFix® S cartridges have the expiry date printed on the label.
--	--

Technical Data

Density	1.7 kg/l (part A+B mixed).
----------------	----------------------------

Curing Speed

Temperature 	Open Time T _{gel} 	Curing Time T _{cur} 
+40°C	1.5 minutes	10 minutes
+35°C - +40°C	1.5 minutes	15 minutes
+30°C - +35°C	2 minutes	20 minutes
+25°C - +30°C	3 minutes	30 minutes
+20°C - +25°C	4 minutes	40 minutes
+10°C - +20°C	6 minutes	80 minutes
+5°C - +10°C	12 minutes	120 minutes
+5°C*	18 minutes	120 minutes

*Min. cartridge temperature = +5°C

Sag Flow	Non-sag, even overhead.
-----------------	-------------------------

Layer Thickness	3 mm max.
------------------------	-----------

Thermal Stability	Glass-Transition Temperature (TG): ~ +90°C (According to ISO75)
--------------------------	--

Mechanical / Physical Properties

Compressive Strength	~ 74 N/mm ² (According to ASTM D695)
-----------------------------	---

Flexural Strength	~24 N/mm ² (7days, +20°C) (According to ASTM D790)
--------------------------	---

Tensile Strength	~12 N/mm ² (7days, +20°C) (According to ASTM D638)
-------------------------	---

E-Modulus	Compressive: ~3'100 N/mm ² (According to ASTM D695)
------------------	---

Design	For design details, please refer to the separate documentation provided: "Technical Documentation Sika AnchorFix® S" Ref: 870 43 03
---------------	---

Resistance

Thermal Resistance	Temperature resistance of the cured adhesive: +50°C long term, +80°C short term (1 - 2 hours)
---------------------------	--

System Information

Application Details

Consumption / Dosage Material consumption per anchor in ml

Thread Ø	Hole Ø	Theoretical volume [ml] @ a certain hole depth [mm]																		
		mm	80	90	110	120	130	140	160	170	180	200	210	220	240	260	280	300	350	400
M8	10	3.4	3.8	4.6	5.0	5.4	5.9	6.7	7.1	7.5	8.4	8.8	9.2	10.1	10.9	11.7	12.6	14.7	16.8	
M10	12	4.4	5.0	6.1	6.6	7.2	7.7	8.8	9.4	9.9	11.0	11.6	12.1	13.2	14.3	15.4	16.5	19.3	22.0	
M12	14	5.6	6.3	7.7	8.4	9.1	9.8	11.2	11.8	12.5	13.9	14.6	15.3	16.7	18.1	19.5	20.9	24.4	27.9	
M14	16	6.9	7.7	9.5	10.3	11.2	12.0	13.8	14.6	15.5	17.2	18.1	18.9	20.6	22.4	24.1	25.8	30.1	34.4	
M14	18	11.2	12.6	15.4	16.8	18.2	19.6	22.4	23.8	25.2	28.0	29.4	30.8	33.6	36.4	39.2	42.0	49.0	56.0	
M16	18	7.8	8.8	10.8	11.8	12.7	13.7	15.7	16.7	17.6	19.6	20.6	21.6	23.5	25.5	27.4	29.4	34.3	39.2	
M16	20	12.6	14.1	17.3	18.8	20.4	22.0	25.1	26.7	28.3	31.4	33.0	34.5	37.7	40.8	44.0	47.1	55.0	62.8	
M20	22	10.8	12.2	14.9	16.2	17.6	18.9	21.6	23.0	24.3	27.0	28.4	29.7	32.4	35.1	37.8	40.5	47.3	54.0	
M20	24	16.6	18.6	22.8	24.8	26.9	29.0	33.1	35.2	37.3	41.4	43.5	45.5	49.7	53.8	58.0	62.1	72.5	82.8	
M20	25	19.7	22.1	27.1	29.5	32.0	34.4	39.4	41.8	44.3	49.2	51.7	54.1	59.0	64.0	68.9	73.8	86.1	98.4	
M24	26	14.2	16.0	19.6	21.4	23.1	24.9	28.5	30.3	32.0	35.6	37.4	39.2	42.7	46.3	49.8	53.4	62.3	71.2	
M27	30	19.4	21.9	26.7	29.2	31.6	34.0	38.9	41.3	43.7	48.6	51.0	53.5	58.3	63.2	68.0	72.9	85.1	97.2	

The indicated filling quantities are calculated without wastage. Wastage 10 - 50%.

The filled quantity can be monitored during injection with the help of the scale on the cartridge label.

Substrate Quality

Mortar and concrete must be at the required strength. No need to be 28 days old. Substrate strength (concrete, masonry, natural stone) must be verified. Pull-out tests must be carried out if the substrate strength is unknown. The anchor hole must always be clean, dry, free from oil and grease etc.. Loose particles must be removed from the holes.

Threaded rods and rebars have to be cleaned thoroughly from any oil, grease or any other substances and particles such as dirt etc..

Application Conditions / Limitations

Substrate Temperature +5°C min. / +40°C max.

Sika AnchorFix® S must be at a temperature of +5°C to +40°C for application.

Ambient Temperature +5°C min. / +40°C max.








Sika AnchorFix® S must be at a temperature of +5°C to +40°C for application.

Application Instructions

Mixing Part A : part B = 10 : 1 by volume

Mixing Tools





Getting the cartridge ready:

380ml	300ml	
		Unscrew and remove the cap
		Cut the film
		Screw on the static mixer
		Place the cartridge into the gun and start application


When the work is interrupted the static mixer can remain on the cartridge after the gun pressure has been relieved. If the resin has hardened in the nozzle when work is resumed, a new nozzle must be attached.

Application Method / Tools

Anchors in solid masonry/concrete:

	Drilling of hole with an electric drill to the diameter and depth required. Drill hole diameter must be in accordance with anchor size.
	The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole. (at least 2x) Important: use oil-free compressors!
	The drill hole must be thoroughly cleaned with the special steel brush (brush at least 2x). The diameter of the brush must be larger than the diameter of the drill hole.
	The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole. (at least 2x) Important: use oil-free compressors!

**..Cont'd..Application
Method / Tools**




The drill hole must be thoroughly cleaned with the special steel brush (brush at least 2x). The diameter of the brush must be larger than the diameter of the drill hole.




The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole. (at least 2x)

Important: use oil-free compressors!



Pump approx. twice until both parts come out uniformly. Do not use this material. Release the gun pressure and clean the cartridge opening with a cloth.



Inject the adhesive into the hole, starting from the bottom, while slowly drawing back the static mixer. In any case avoid entrapping air. For deep holes extension tubing can be used.



Insert the anchor with a rotary motion into the filled drill hole. Some adhesive must come out of the hole.


Important: the anchor must be placed within the open time.

Anchors in hollow blocks:




Drilling of hole with an electric drill to the diameter and depth required. Drill hole diameter must be in accordance with anchor- and perforated sleeve size.

Note: with hollow material do not use rotary hammer drills.




The drill hole must be thoroughly cleaned with a round brush (brush at least 1x). The diameter of the brush must be larger than the diameter of the drill hole.



The drill hole must be cleaned after each cleaning step with a blow pump or by compressed air, starting from the bottom of the hole (pump at least 1x).


Important: use oil-free compressors!




Insert perforated sleeve completely into the drill hole.




Pump approx. twice until both parts come out uniformly. Do not use this material. Release the gun pressure and clean the cartridge opening with a cloth.



Inject the adhesive into the perforated sleeve, starting from the bottom, while slowly drawing back the static mixer. In any case avoid entrapping air.



Close the cap from the perforated sleeve to avoid some escape of the resin during entering the steel rod.



Insert the anchor with a rotary motion into the filled perforated sleeve. Use the adequate steel rod size.

Important: the anchor must be placed within the open time.



During the resin hardening time the anchor must not be moved or loaded. Wash tools immediately with Sika® Colma Cleaner. Wash hands and skin thoroughly with warm soap water.

Cleaning of Tools

Clean tools and application equipment with Sika® Colma Cleaner immediately after use. Hardened / cured material can only be mechanically removed.

Value Base

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Local Restrictions

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



Sika Singapore Pte Ltd
200 Pandan Loop, 06-02 Pantech 21
Singapore 128388
SINGAPORE

Phone: +65 6777 2811
Fax: +65 6779 6200
e-mail: info@sg.sika.com
www.sika.com.sg



Sika Kimia Sdn Bhd
Lot 689 Nilai Industrial Estate
71800 Nilai, Negeri Sembilan DK
MALAYSIA

Phone: +606-7991762
Fax: +606-7991980
e-mail: info@my.sika.com
www.sika.com.my

