

SikaScreed®-20 EBB

Epoxy bonding agent

Product Description

SikaScreed®-20 EBB is a moisture tolerant, structural, two part bonding agent, based on a combination of epoxy resins and special fillers.

Uses

As a structural bonding agent and adhesive for SikaScreed® HardTop product range and for hardened concrete:

As a structural bonding agent and adhesive for

- Concrete elements (including bonding fresh to hardened concrete)
- Hard natural stone
- Ceramics, fibre-cement
- Mortar, Bricks, Masonry
- Steel, Iron, Aluminium
- Wood
- Polyester / fibreglass and Epoxy resin materials
- Glass

Characteristics / Advantages

- Easy to mix and apply
 - Suitable for dry and damp concrete surfaces
 - Very good adhesion to most construction materials
 - High Bond Strength
 - Hardens without shrinkage
 - High initial and ultimate mechanical strength
-

Construction



Mechanical / Physical Properties

Compressive Strength*

(According to ASTM D 695-95)

Curing time	Curing temperature		
	+10°C	+23°C	+30°C
1 day	-	~24 N/mm ²	~30 N/mm ²
3 days	~13 N/mm ²	~28 N/mm ²	~41 N/mm ²
7 days	~32 N/mm ²	~39 N/mm ²	~52 N/mm ²
14 days	~42 N/mm ²	~49 N/mm ²	~56 N/mm ²

*at 4% elongation

Flexural Strength

(According to DIN EN ISO 178)

Curing time	Curing temperature		
	+10°C	+23°C	+30°C
1 day	-	~29 N/mm ²	~52 N/mm ²
3 days	~12 N/mm ²	~48 N/mm ²	~57 N/mm ²
7 days	~24 N/mm ²	~50 N/mm ²	~60 N/mm ²
14 days	~42 N/mm ²	~56 N/mm ²	~65 N/mm ²

Tensile Strength

(According to ISO 527)

Curing time	Curing temperature		
	+10°C	+23°C	+30°C
1 day	-	~16 N/mm ²	~24 N/mm ²
3 days	-	~25 N/mm ²	~30 N/mm ²
7 days	~20 N/mm ²	~32 N/mm ²	~33 N/mm ²
14 days	~25 N/mm ²	~33 N/mm ²	~34 N/mm ²

Bond Strength

(According to EN ISO 4624, EN 1542 and EN 12188)

Time	Temperature	Substrate	Bond strength
7 days	+10°C	Concrete dry	> 3 N/mm ² *
7 days	+10°C	Concrete moist	> 3 N/mm ² *
1 day	+10°C	Steel	6 - 10 N/mm ²
3 days	+10°C	Steel	10 - 14 N/mm ²
3 days	+23°C	Steel	11 - 15 N/mm ²
3 days	+30°C	Steel	13 - 17 N/mm ²

*100% concrete failure.

E-Modulus

Tensile:

~ 4'000 N/mm² (14 days at +23°C)

(According to ISO 527)

Compressive:

~ 3'250 N/mm² (14 days at +23°C)

(According to ASTM D695-95)

Elongation at Break

1.0 ± 0.1% (24 days at +23°C)

(According to ISO 527)

System Information

Application Details

Consumption / Dosage Sika® Screed-20 EBB:
For substrate roughness until 1.0mm and normal absorbency ca. 0.6-1.0 kg/m².
For higher substrate roughness and/or stronger absorbency the consumption has to be located with a test area on side.

Substrate Quality Hardened mortar and concrete must be older than 28 days (depending on any minimal strength requirements).
Verify the substrate strength by testing (concrete, masonry, natural stone).
The substrate surface (all types) must be clean, dry or mat damp (no standing water) and free from contaminants such as dirt, oil, grease, existing surface treatments and coatings etc.
Steel substrates must be de-rusted to a condition similar to SA 2.5.
The substrate must be sound and all loose or friable particles must be removed.

Substrate Preparation Concrete, mortar, stone and brick substrates.:
Concrete and other hardened mineral substrates must be prepared by suitable means such as high pressure water jetting and / or blast cleaning, in order to obtain surfaces that are sound, clean, dry or mat damp (no standing water) and free from any cement laitance, ice, grease, oils, old coatings or other surface treatments. Any loose or friable particles must also be removed to achieve a contaminant free and open textured surface.
Steel substrates:
Steel surfaces must be cleaned and prepared thoroughly to the acceptable quality standard equivalent to Sa 2.5 i.e. normally by blast cleaning and then removing any dust by vacuum. Avoid dew point conditions.

Application Conditions / Limitations

Substrate Temperature +10°C min. / +30°C max.
Ambient Temperature +10°C min. / +30°C max.
Material Temperature SikaScreed®-20 EBB must be applied at temperatures between +10°C and +30°C
Substrate Moisture Content Substrate must be dry or mat damp (no standing water)
Brush the material well into the substrate
Dew Point Beware of condensation and dew point conditions!
Substrate temperature during application must be at least 3°C above dew point.

Application Instructions

Mixing Part A : part B = 2 : 1 by weight or volume

Mixing Time



Pre batched units:
Mix parts A+B together for at least 3 minutes with a mixing spindle attached to a slow speed electric drill (max. 300 rpm) until the material becomes smooth in consistency and a uniform grey colour. Avoid aeration while mixing. Then, pour the whole mix into a clean container and stir again for approx. 1 more minute at low speed to keep air entrapment at a minimum. Mix only that quantity which can be used within its pot life.

Application Method / Tools

Apply the mixed SikaScreed®-20 EBB to the prepared surface by brush, roller, spray or with a trowel, and ensure uniform and complete coverage. On hardened concrete substrates mechanically prepared to receive fresh concrete, always apply by brush and work the material well into the substrate.
Place the fresh concrete whilst the SikaScreed®-20 EBB layer is still 'tacky'. If the material becomes glossy and loses tackiness, apply a fresh coat with additional SikaScreed®-20 EBB and proceed.

Cleaning of Tools	Clean all tools and application equipment with Sika® Colma Cleaner immediately after use. Hardened / cured material can only be mechanically removed.								
Pot-life	(Pot life According to EN ISO 9514) <table border="1"> <thead> <tr> <th>Temperature</th> <th>+10°C</th> <th>+20°C</th> <th>+30°C</th> </tr> </thead> <tbody> <tr> <td>Pot life (200 g)</td> <td>~ 145 minutes</td> <td>~ 55 minutes</td> <td>~ 35 minutes</td> </tr> </tbody> </table> <p>The pot-life begins when the resin and hardener are mixed. It is shorter at high temperatures and longer at low temperatures. The greater the quantity mixed, the shorter the pot-life. To obtain longer workability at high temperatures, the mixed SikaScreed®-20 EBB may be divided into portions. Another method is to chill parts A+B before mixing them (not below +5°C).</p>	Temperature	+10°C	+20°C	+30°C	Pot life (200 g)	~ 145 minutes	~ 55 minutes	~ 35 minutes
Temperature	+10°C	+20°C	+30°C						
Pot life (200 g)	~ 145 minutes	~ 55 minutes	~ 35 minutes						
Waiting time / Overcoating	Maximum waiting time for wet-in-wet application on SikaScreed®-20 EBB +10°C 3h +20°C 1 +30°C 30min								
Notes on Application / Limitations	SikaScreed®-20 EBB is formulated to have low creep under permanent loading. However due to the creep behaviour of all polymer materials under load, the long term structural design load must account for creep. Generally the long term structural design load must be lower than 20-25% of the failure load. Please consult a structural engineer for load calculations for your specific application.								
Value Base	All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.								
Local Restrictions	Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.								
Health and Safety Information	For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.								
Legal Notes	The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.								



Sika Österreich GmbH
Dorfstrasse 23
AT-6700 Bludenz
Österreich

Phone +43 50 610-0
Telefax +43 50 610-1901
www.sika.at