

Product Data Sheet
Edition 25/07/2014
Identification no:
02 08 01 05 002 0 000004
Sikafloor®-14 Pronto

(Template for local translation, only for internal use)

Sikafloor®-14 Pronto

2-part PMMA binder for self-smoothing screed and levelling mortars based on reactive acrylic resins

Product Description

Sikafloor®-14 Pronto is a two part, fast curing self-smoothing binder based on reactive acrylic resins for the Sikafloor®-Pronto Modular System.

Sikafloor®-14 Pronto consists of:

Part A: Sikafloor®-14 Pronto Resin

Part B: Sika®-Pronto Hardener

Sikafloor®-Pronto Filler

Sika®-Pronto Pigment is used to colour Sikafloor®-14 Pronto if required.

Uses

- For fast curing mechanically and chemically resistant coatings with layer thickness of 2 to 4 mm
- Particularly suitable for the beverage and food industry
- For fast overcoating of intermediate decks and ramps in multi-storey and underground car-parks
- Skid resistant and multi-coloured surfaces can be obtained by broadcasting with coloured quartz sand or coloured chips

Characteristics / Advantages

- Very fast curing, even at low temperatures
- Good mechanical and chemical resistance
- Solvent-free
- Part of a complete modular system

Test

Approval / Standards

Certificate of conformity , 34913 U 13 , Isega Germany, January 2013
2-part PMMA binder for self-smoothing screed and levelling mortars based on reactive acrylic resins according to EN 1504-2: 2004 and EN 13813:2002, DoP 02 08 01 05 002 0 000004 1131, certified by Factory Production Control Body No. 0921, certificate 1119, and provided with the CE-mark

Product Data

Form

Appearance / Colours

Part A: Sikafloor®-14 Pronto: transparent, bluish liquid
Part B: Sika®-Pronto Hardener: white, powder
Sikafloor®-Pronto Filler: white, fine aggregates

Sika®-Pronto Pigment:
~ RAL 7032 other colours upon request.

Packaging

Part A: Sikafloor®-14 Pronto: 25 kg containers , 200 kg drums
Part B: Sika®-Pronto Hardener: 1.0 kg packs (in 0.1 kg bags)
Sikafloor®-Pronto Filler: 25 kg packs
Sika®-Pronto Pigment: 5 kg packs (10 x 0.5 kg bags)



Storage

Storage Conditions / Shelf Life

From date of production if stored properly in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5°C and +30°C.

Part A: Sikafloor®-14 Pronto: 12 months
Part B: Sika®-Pronto Hardener: 6 months
Sikafloor®-Pronto Filler for an unlimited period
Sika®-Pronto Pigment 2 years

Sikafloor®-Pronto Hardener must be protected from heat, direct sunlight, moisture and impact.

Technical Data

Chemical Base Reactive acrylic resins

Density ~ 0.99 kg/l (at +23°C) (DIN 51 757)

Solid Content ~ 100% (by volume) / ~ 100% (by weight)

Mechanical / Physical Properties

Compressive Strength Resin filled: ~ 40 N/mm² (14 days / +23°C) (DIN 1164)

Flexural Strength Resin filled: ~ 25 N/mm² (14 days / +23°C) (DIN 1164)

Shore D Hardness Resin: ~ 62 (DIN 53 505)

Resistance

Chemical Resistance Resistant to many chemicals. Please ask for a detailed chemical resistance table.

Thermal Resistance

Exposure*	Dry heat
Permanent	+50°C
Short-term max. 2d	+60°C
Short-term max. 1h	+80°C

Short-term moist/wet heat* up to +80°C where exposure is only occasional (steam cleaning etc.)

* No simultaneous chemical and mechanical exposure and only in combination with Sikafloor®-13 / -16 / -17 Pronto as a broadcast system with approx. 3 - 4 mm thickness.

System Information

System Structure

Scratch coat / levelling mortar (surface roughness up to 3 mm):

Primer: 1 x Sikafloor®-10 / -11 / -13 Pronto
 Scratch coat: 1 x Sikafloor®-14 Pronto + quartz sand (0.1 - 0.3 mm) + Extender T

Broadcast system approx. 2 - 4 mm for dry interior areas:

Primer: 1 x Sikafloor®-10 / -11 / -13 Pronto
 Base coat: 1 x Sikafloor®-14 Pronto
 Broadcasting: quartz sand (0.4 - 0.7 mm or 0.7 - 1.2 mm), coloured quartz sand (0.3 - 0.8 mm or 0.6 - 1.2 mm) or coloured chips, broadcast to excess
 Seal coat: 1 - 2 x Sikafloor®-16 Pronto

Broadcast system approx. 3 - 4 mm for wet areas, flexible:

Primer: 1 x Sikafloor®-10 / -11 / -13 Pronto
 Membrane: 1 x Sikafloor®-15 Pronto
 Base coat: 1 x Sikafloor®-14 Pronto
 Broadcasting: quartz sand (0.7 - 1.2 mm) or coloured quartz sand (0.6 - 1.2 mm), broadcast to excess
 Seal coat: 1 - 2 x Sikafloor®-17 Pronto

Broadcast system approx. 2 - 4 mm for interior :

Primer: 1 x Sikafloor®-10 / -11 / -13 Pronto
 Base coat: 1 x Sikafloor®-14 Pronto
 Broadcasting: quartz sand (0.7 - 1.2 mm) or coloured quartz sand (0.6 - 1.2 mm), broadcast to excess
 Seal coat: 1 - 2 x Sikafloor®-18 Pronto

Broadcast system approx. 3 - 4 mm for interior , flexible:

Primer: 1 x Sikafloor®-10 / -11 / -13 Pronto
 Membrane: 1 x Sikafloor®-15 Pronto
 Base coat: 1 x Sikafloor®-14 Pronto
 Broadcasting: quartz sand (0.7 - 1.2 mm) or coloured quartz sand (0.6 - 1.2 mm), broadcast to excess
 Seal coat: 1 - 2 x Sikafloor®-18 Pronto

Application Details

Consumption	Coating System	Product	Consumption
	Primer	Sikafloor®-10 / -11 / -13 Pronto	0.4 - 0.5 kg/m ²
	Levelling Mortar (surface roughness max 3 mm)	1 pbw Sikafloor®-14 Pronto (without Filler), 1.5 - 2.0 pbw quartz sand (0.1 - 0.3 mm), 0.01 - 0.02 pbw Extender T	~ 1.5 kg/m ² /mm (0.5 kg part A + 1 kg quartz sand + 0.01 kg Extender T)
	Broadcast base coat using quartz sand or coloured quartz sand (film thickness ~ 2 - 4 mm)	Sikafloor®-14 Pronto inclusive Filler, Hardener and (optional) Pigment (refer to mixing table) broadcast with quartz sand or coloured quartz sand	1.5 - 4.0 kg/m ² ~ 4.0 kg/m ²
	Broadcast base coat using coloured chips (film thickness ~ 3 - 4 mm)	Sikafloor®-14 Pronto inclusive Filler, Hardener and (optional) Pigment (refer to mixing table) broadcast with colour chips	5.0 kg/m ² ~ 0.5 kg/m ²
	Seal coat (dry interior areas)	Sikafloor®-16 Pronto	~ 0.6 - 0.8 kg/m ² in 1 to 2 coats
	Coloured Seal coat (interior)	Sikafloor®-18 Pronto (incl. Pigment if required)	~ 0.6 - 0.8 kg/m ² in 1 to 2 coats
	Seal coat (permanent or part-time (approx. >25%) wet areas)	Sikafloor®-17 Pronto	1 st coat: 0.5 - 0.6 kg/m ² 2 nd coat: 0.3 - 0.4 kg/m ² (optional)

These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc.

Substrate Quality	<p>The cementitious substrate must be sound and of sufficient compressive strength (min. 25 N/mm²) with a minimum pull-off strength 1.5 N/mm².</p> <p>The substrate must be clean dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc.</p> <p>The application of a trial area is mandatory to ensure the compatibility of the substrate and the proposed Sikafloor Pronto System, especially when cementitious substrates treated with a curing agent</p>
Substrate Preparation	<p>Concrete substrates must be prepared mechanically using abrasive blast cleaning or scarifying equipment to remove cement laitance and achieve an open textured surface.</p> <p>Weak concrete must be removed and surface defects such as blowholes and voids must be fully exposed.</p> <p>Repairs to the substrate, filling of blowholes/voids and surface levelling must be carried out using appropriate products from the Sikafloor[®], SikaDur[®] and SikaGard[®] range of materials.</p> <p>The concrete or screed substrate has to be primed or levelled in order to achieve an even surface.</p> <p>High spots must be removed by e.g. grinding.</p> <p>All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush and/or vacuum.</p>

Application Conditions / Limitations

Substrate Temperature	0°C min. / +30°C max.
Ambient Temperature	0°C min. / +30°C max.
Substrate Moisture Content	<p>≤ 4% pbw moisture content.</p> <p>Test method: Sika[®]-Tramex meter, CM - measurement or Oven-dry-method.</p> <p>No rising moisture according to ASTM (Polyethylene-Sheet).</p>
Relative Air Humidity	~ 80% r.h. max.
Dew Point	<p>Beware of condensation!</p> <p>The substrate and uncured floor must be at least 3°C above dew point to reduce the risk of condensation or blooming on the floor finish.</p>

Application Instructions

Mixing *Self-smoothing screed and levelling mortar:*

Part A : Part C : Pigment = 12.5 : 25 : 1 (by weight)

The amount of Hardener required is dependent on the ambient- and substrate temperature (see table below).

Sikafloor [®] -14 Pronto 12.5 kg	Sika [®] -Pronto Hardener				Sikafloor [®] -Pronto Filler	Sika [®] -Pronto Pigment
	0°C	+10°C	+20°C	+30°C		
Sika [®] -Pronto Hardener (%pbw)	750 g (6.0%)	500 g (4.0%)	375 g (3.0%)	250 g (2.0%)	25 kg	1 kg

Seal coat (underneath Sikafloor[®]-16 Pronto):

Part A : Pigment = 9 : 1 (by weight)

The amount of Hardener required is dependent on the ambient- and substrate temperature (see table below).

Sikafloor [®] -14 Pronto	Sika [®] -Pronto Hardener			
	0°C	+10°C	+20°C	+30°C
Sika [®] -Pronto Hardener	6.0%	4.0%	3.0%	2.0%

	<p>The hardener powder can also be ordered under the product name „Perkadox CH 50 X“ by Akzo Nobel, www.akzonobel.com, “Interox BP-50 FT” by Degussa, www.degussa.com or “BP 50 W+” by Pergan GmbH, www.pergan.com.</p>
Mixing Time	<p>Mix part A thoroughly, then add the Sikafloor®-Pronto Filler, and (if required) the Sika®-Pronto Pigment and mix for at least 1 minute. When the different components are adequately mixed, add the Hardener in the correct quantity and mix for a further 1 minute.</p> <p>Over mixing must be avoided to minimise air entrainment.</p> <p>For ease of handling, 25 kg units may be split (2 x 12.5 kg) (refer to Mixing table). Always weigh out components.</p>
Mixing Tools	<p><i>For indoor work, spark free mixing equipment must be used (explosion-proof)!</i></p> <p>Sikafloor®-14 Pronto must be thoroughly mixed using a low speed electric stirrer (300 - 400 rpm) or other suitable equipment.</p>
Application Method / Tools	<p>Prior to application, confirm substrate moisture content, r.h. and dew point.</p> <p>For external applications, apply on a falling temperature. If applied during rising temperatures “pin holing” may occur from rising air.</p> <p><i>Levelling:</i> Rough surfaces need to be levelled first. Therefore use e.g. Sikafloor®-14 Pronto or Sikadur®-12 Pronto levelling mortar (see PDS). Apply by squeegee / trowel to the required thickness.</p> <p><i>Broadcast base coat:</i> Sikafloor®-14 Pronto is poured, spread evenly by means of a serrated trowel. Roll immediately in one direction with a spiked roller to ensure even thickness and to remove entrapped air. Immediately afterwards, broadcast with quartz sand.</p> <p>Note: broadcast quartz sand in ca. three steps, which means the first couple of times broadcast slightly, then to excess in order to ensure an even distribution of quartz sand and to avoid displacing of the material.</p> <p>A multi coloured surface can be obtained by broadcasting with coloured-chips or coloured-quartz. (The compatibility of the coloured-chips to PMMA-systems must be checked prior to application).</p> <p>The material cures very quickly and therefore application must be carried out steadily and “wet on wet” in order to achieve joint free floors.</p>
Cleaning of Tools	<p>Clean all tools and application equipment with Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically.</p>

Potlife	0°C	+10°C	+20°C	+30°C
	~ 20	~ 20	~ 15	~ 10

Waiting Time / Overcoating

Before applying Sikafloor®-14 Pronto on Sikafloor®-13 / -11 Pronto allow:

Substrate temperature	0°C	+10°C	+20°C	+30°C
Minimum(minutes)	50	45	40	35
Maximum (minutes)	*	*	*	*

Before applying Sikafloor®-14 Pronto on Sikafloor®-10 Pronto allow:

Substrate temperature	0°C	+10°C	+20°C	+30°C
Minimum(minutes)	70	50	50	35
Maximum (minutes)	*	*	*	*

Before applying Sikafloor®-14 Pronto on Sikafloor®-15 Pronto allow:

Substrate temperature	+5°C	+10°C	+15°C	+20°C	+25°C	+30°C
Minimum(minutes)	80	60	50	45	35	30
Maximum (minutes)	*	*	*	*	*	*

Before applying Sikafloor®-14 Pronto / -16 Pronto / -17 Pronto on Sikafloor®-14 Pronto allow:

Substrate temperature	0°C	+10°C	+20°C	+30°C
Minimum(minutes)	80	60	45	35
Maximum (minutes)	*	*	*	*

*No time limit, the Sikafloor®-Pronto materials can be applied on each other after thorough clean

Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.

Notes on Application / Limitations

Do not use Sikafloor®-14 Pronto on substrates with rising moisture.

In case of broadcast systems with a finer quartz sand, e.g. 0.4 - 0.7 mm, curing defects may occur which may require additional hardener. A trial area is mandatory.

Freshly applied Sikafloor®-14 Pronto must be protected from damp, condensation and water for at least 1 hour.

Use spark proof mixing equipment for internal applications.

Always ensure good ventilation when using Sikafloor®-14 Pronto in a confined space.

In order to ensure optimum curing during internal applications the air must be exchanged at least seven times per hour. During application and curing use a forced fresh air supply/exhausting of fumes with appropriate equipment (explosion-proof).

Systems based on reactive acrylic resins exhibit a characteristic odour during application and prior to achieving full cure, once fully cured they are taint free. All unpackaged goods should be removed from the area of the works during application. Do not apply in the presence of foodstuffs. Any foodstuffs, whether packaged or not, should be completely isolated from the flooring works during the application process and until the products are fully cured.

Tools

Recommended Supplier of Tools:

PPW-Polyplan-Werkzeuge GmbH, Phone: +49 40/5597260, www.polyplan.com

Serrated trowel for smooth wearing layer:

e.g. Large-Surface Scraper No. 565, Toothed blades No. 25

The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.

Under certain conditions, underfloor heating or high ambient temperatures combined with high point loading, may lead to imprints in the resin.

If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

Curing Details

Applied Product ready for use

	0°C	+10°C	+20°C	+30°C
Foot traffic (minutes)	~ 80	~ 60	~ 45	~ 35
Full cure (hours)	~ 3	~ 3	~ 2	~ 2

Times are approximate and will be affected by changing ambient conditions.

Value Base

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Local Restrictions

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

EU Regulation 2004/42 VOC - Decopaint Directive

According to the EU-Directive 2004/42, the maximum allowed content of VOC (Product category IIA / j type **sb**) is 500 g/l (Limit 2010) for the ready to use product. The maximum content of **Sikafloor®-14 Pronto** is < 500 g/l VOC for the ready to use product.



Sika Services AG
Tüffenwies 16
CH-8048 Zurich
Switzerland

Phone +41 44 436 40 40
Telefax +41 44 436 46 86
www.sika.com

