

(Template for local translation, only for internal use)

Sikafloor®-17 Pronto

2-part seal coat for wet areas or cold storage rooms
based on reactive acrylic resins

Product Description

Sikafloor®-17 Pronto is a two part, fast curing, flexible seal coat based on reactive acrylic resins for the Sikafloor®-Pronto Modular System.

Sikafloor®-17 Pronto consists of:

Part A: Sikafloor®-17 Pronto resin

Part B: Sika®-Pronto Hardener

Sika®-Pronto Pigment is used to colour Sikafloor®-17 Pronto where required.

Uses

- Seal coat for broadcast layers of the Sikafloor®-Pronto Modular System (wet areas or cold storage rooms)
- Seal coat for broadcast screeds prepared of e.g. Sikafloor®-81 EpoCem or Sikafloor®-263 SL if broadcast to excess (wet areas or cooling rooms)
- Particularly suitable for food industry use

Characteristics / Advantages

- Very fast curing, even at low temperatures
- Good mechanical and chemical resistance
- Good UV-resistance
- Solvent-free
- Part of a complete modular system

Test

Approval / Standards

Conforms to the requirements of DIN 51130 (Skid / slip resistance).

Certificate of conformity , 34913 U 13 , Isega Germany, January 2013

2-part seal coat for wet areas and cold storage rooms based on reactive acrylic resins according to EN 1504-2: 2004 and EN 13813:2002, DoP 02 08 01 05 007 0 000001 1131, certified by Factory Production Control Body No. 0921, certificate 1119, and provided with the CE-mark

Product Data

Form

Appearance/Colours

Part A: Sikafloor®-17 Pronto: transparent, bluish liquid
Part B: Sika®-Pronto Hardener: white, powder

Sika®-Pronto Pigment:
~ 7032 other colours upon request.

Packaging

Part A: Sikafloor®-17 Pronto: 25 kg containers, 200 kg drums
Part B: Sika®-Pronto Hardener: 1.0 kg packs (in 0.1 kg bags)
Sika®-Pronto Pigment: 5 kg packs (10 x 0.5 kg bags)

Construction



Storage

Storage Conditions / Shelf Life

From date of production if stored properly in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5°C and +30°C:

Part A: Sikafloor®-17 Pronto: 12 months
Part B: Sika®-Pronto Hardener: 6 months
Sika®-Pronto Pigment 2 years

Sikafloor®-Pronto Hardener must be protected from heat, direct sunlight, moisture and impact.

Technical Data

Chemical Base

Reactive acrylic resins

Density

~ 0.98 kg/l (at +23°C)

(DIN 51 757)

Solid Content

~ 100% (by volume) / ~ 100% (by weight)

Resistance

Chemical Resistance

Resistant to many chemicals. Please ask for a detailed chemical resistance table.

Thermal Resistance

Exposure*	Dry heat
Permanent	+50°C
Short-term max. 1h	+80°C

Short-term moist/wet heat* up to +80°C where exposure is only occasional (steam cleaning etc.)

*No simultaneous chemical and mechanical exposure and only in combination with Sikafloor®-14 / 15 Pronto as a broadcast system with approx. 3 - 4 mm thickness.

System Information

System Structure

Sealing of broadcast screed:

Broadcast system approx. 3 - 4 mm for wet areas:

Primer: 1 x Sikafloor®-10 / -11 / -13 Pronto
Base coat: 1 x Sikafloor®-14 Pronto
Broadcasting: quartz sand (0.7 - 1.2 mm) or
coloured quartz sand (0.6 - 1.2 mm), broadcast to excess
Seal coat: 1 - 2 x Sikafloor-17 Pronto

Broadcast system approx. 3 - 4 mm for cold storage rooms, flexible:

Primer: 1 x Sikafloor®-10 / -11 / -13 Pronto
Base coat: 1 x Sikafloor®-15 Pronto
Broadcasting: quartz sand (0.7 - 1.2 mm) or
coloured quartz sand (0.6 - 1.2 mm),
broadcast to excess
Seal coat: 1 - 2 x Sikafloor®-17 Pronto

Broadcast system approx. 3 - 4 mm for wet areas, flexible:

Primer: 1 x Sikafloor®-10 / -11 / -13 Pronto
Membrane: 1 x Sikafloor®-15 Pronto
Base coat: 1 x Sikafloor®-14 Pronto
Broadcasting: quartz sand (0.7 - 1.2 mm) or
coloured quartz sand (0.6 - 1.2 mm), broadcast to excess
Seal coat: 1 - 2 x Sikafloor®-17 Pronto

Also suitable for sealing of e.g. Sikafloor®-263 SL and Sikafloor®-81 EpoCem if fully broadcast.

Application Details

Consumption

Coating System	Product	Consumption
Transparent seal coat onto Sikafloor-14 Pronto broadcast systems for wet areas	Sikafloor®-17 Pronto	1 st coat: 0.5 - 0.6 kg/m ² 2 nd coat: 0.3 - 0.4 kg/m ² (optional)
Coloured seal coat onto Sikafloor-14 Pronto broadcast systems for wet areas	Sikafloor®-17 Pronto (9 pbw)+ Sika®-Pronto Pigment (1 pbw)	1 st coat: 0.5 - 0.6 kg/m ² 2 nd coat: 0.3 - 0.4 kg/m ² (optional)
Transparent seal coat onto Sikafloor-15 Pronto broadcast systems for flexible Pronto systems for wet or cold storage areas	Sikafloor-17 Pronto	1 st coat: 0.5 - 0.6 kg/m ² 2 nd coat: 0.3 - 0.4 kg/m ² (optional)
Coloured seal coat onto Sikafloor-15 Pronto broadcast systems for flexible Pronto systems for wet or cold storage areas	Sikafloor®-17 Pronto (9 pbw) + Sika®-Pronto Pigment (1 pbw)	1 st coat: 0.5 - 0.6 kg/m ² 2 nd coat: 0.3 - 0.4 kg/m ² (optional)

These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc.

Substrate Quality

The substrate must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc.

Pull-off strength shall be not less than 1.5 N/mm²

The application of a trial area is mandatory to ensure the compatibility of the substrate and the proposed Sikafloor Pronto System, especially when cementitious substrates treated with a curing agent.

Substrate Preparation

All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush or vacuum.

Application Conditions / Limitations

Substrate Temperature 0°C min. / +30°C max.

Ambient Temperature 0°C min. / +30°C max.

Relative Air Humidity ~ 80% r.h. max.

Dew Point Beware of condensation!

The substrate and uncured floor must be at least 3°C above dew point to reduce the risk of condensation or blooming on the floor finish.

Application Instructions

Mixing

Part A : Pigment = 9 : 1 (by weight)

The amount of Hardener required is dependent on the ambient- and substrate temperature (see table below).

Sikafloor®-17 Pronto 9 kg	Sika-Pronto Hardener			
	0°C	+10°C	+20°C	+30°C
Sika®-Pronto Hardener (%pbw)	270 g (3.0%)	180 g (2.0%)	90 g (1.0%)	90 g (1.0%)

The hardener powder can also be ordered under the product name „Perkadox CH 50 X“ by Akzo Nobel, www.akzonobel.com or “Interox BP-50 FT” by Degussa, www.degussa.com or “BP 50 W+” by Pergan GmbH, www.pergan.com.

Mixing Time Mix part A thoroughly then add the Hardener in the correct quantity and mix for a further 1 minute.

Pigmented: Mix part A thoroughly. Premix the required amount of Sika-Pronto Pigment with the same quantity of part A by dissolver. Mix part A and the obtained pigment powder (overall content of Sika-Pronto Pigment in the mixture = 10%) for at least 3 minutes. Then add the Hardener in the correct quantity and mix for a further 1 minute.

Over mixing must be avoided to minimise air entrainment.

For ease of handling, 25 kg units may be split (refer to Mixing table). Always weigh out components.

Mixing Tools *For indoor work, spark-free mixing equipment must be used (explosion-proof)!*

Sikafloor®-17 Pronto must be thoroughly mixed using a low speed electric stirrer (300 - 400 rpm) or other suitable equipment.

For the preparation of the pigment powder, a dissolver must be used.

Application Method / Tools Prior to application confirm r.h. and dew point.

For external applications, apply on a falling temperature. If applied during rising temperatures “pin holing” may occur from rising air.

Seal coat:
Immediately after mixing, pour the Sikafloor®-17 Pronto onto the substrate and spread evenly by means of a “non-fuzzing” short-pile nylon roller or squeegee *and then back-rolled (crosswise) with a short-piled roller.-*

A seamless finish can be achieved if a ‘wet’ edge is maintained during application.

Cleaning of Tools Clean all tools and application equipment with Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically.

Potlife

	0°C	+10°C	+20°C	+30°C
Time (minutes)	~ 20	~ 20	~ 15	~ 8

Waiting Time / Overcoating

Before applying Sikafloor®-17 Pronto on Sikafloor®-14 / -15 Pronto allow:

Substrate temperature	0°C	+10°C	+20°C	+30°C
Minimum (minutes)	80	60	45	35
Maximum (minutes)	*	*	*	*

Before applying Sikafloor®-17 Pronto on Sikafloor®-17 Pronto allow:

Substrate temperature	0°C	+10°C	+20°C	+30°C
Minimum (minutes)	50	50	40	30
Maximum (minutes)	*	*	*	*

*No time limits, the Sikafloor®-Pronto materials can be applied on each other after thorough cleaning

Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.

For application on fully broadcast Sikafloor®-263 SL or similar screeds refer to the PDS of this material.

Notes on Application / Limitations

Freshly applied Sikafloor®-17 Pronto must be protected from damp, condensation and water for at least 1 hour.

Use spark proof mixing equipment for internal applications.

Always ensure good ventilation when using Sikafloor®-17 Pronto in a confined space.

For areas without frequent water load (approx. > 25% of time) or dry areas with temperatures > 0°C use Sikafloor-16 Pronto as a seal coat.

In order to ensure optimum curing during internal applications the air must be exchanged at least seven times per hour. During application and curing use a forced fresh air supply / exhausting of fumes with appropriate equipment (spark-free / explosion-proof).

Unevenness of substrates as well as inclusions of dirt cannot be covered by thin sealer coats. Therefore substrate and adjacent areas must be cleaned thoroughly prior to application.

Systems based on reactive acrylic resins exhibit a characteristic odour during application and prior to achieving full cure, once fully cured they are taint free. All unpackaged goods should be removed from the area of the works during application. Do not apply in the presence of foodstuffs. Any foodstuffs, whether packaged or not, should be completely isolated from the flooring works during the application process and until the products are fully cured.

Tools

Recommended supplier of tools:

PPW-Polyplan-Werkzeuge GmbH, Phone: +49 40/5597260, www.polyplan.com

For exact colour matching, ensure the Sika®-Pronto Pigment in each area is applied from the same control batch number.

Under certain conditions, underfloor heating or high ambient temperatures combined with high point loading, may lead to imprints in the resin.

If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

Curing Details

Applied Product ready for use

	0°C	+10°C	+20°C	+30°C
Foot traffic (minutes)	~ 50	~ 50	~ 40	~ 30
Full cure (hours)	~ 2	~ 2	~ 1	~ 1

Note: Times are approximate and will be affected by changing ambient conditions

Cleaning / Maintenance

Methods

To maintain the appearance of the floor after application, Sikafloor®-17 Pronto must have all spillages removed immediately and be regularly cleaned using rotary brush, mechanical scrubbers, scrubber dryer, high pressure washer, wash and vacuum techniques etc. using suitable detergents and waxes.

Value Base

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Local Restrictions

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

EU Regulation 2004/42

According to the EU-Directive 2004/42, the maximum allowed content of VOC (Product category IIA / j type **sb**) is 500 g/l (Limit 2010) for the ready to use product.

VOC - Decopaint Directive

The maximum content of **Sikafloor®-17 Pronto** is < 500 g/l VOC for the ready to use product.



Sika Services AG
Tüffenwies 16
CH-8048 Zurich
Switzerland

Phone +41 44 436 40 40
Telefax +41 44 436 46 86
www.sika.com

