

PRODUCT DATA SHEET

SikaSeal®-623 Fire+

Fire resistant intumescent sealant for penetration seals

DESCRIPTION

SikaSeal®-623 Fire+ is a fire resistant, intumescent graphite sealant. It is used for penetration seals around combustible services in fire compartment walls and floors. In case of fire, SikaSeal®-623 Fire+ closes gaps due to volume expansion of up to 25 times.

USES

- Restores the fire resistance performance of a wall or a floor which incorporates combustible pipes, combustible pipe insulations or conduits.
- Can be used in combination with SikaSeal®-626 Fire Board+, refer to certificates

FEATURES

- Up to 4 hours fire resistance depending on the configuration
- Highly intumescent - volume expansion up to 25 times original size
- 1-part ready to use, easy to apply
- Provides acoustic insulation

SUSTAINABILITY

- Conformity with LEED v4 EQc 2: Low-Emitting Materials
- VOC emission classification GEV-EMICODE EC 1^{PLUS}

APPROVALS / CERTIFICATES

- CE Marking and Declaration of Performance based on European Technical Assessment ETA 23/0963, based on EAD 350454-00-1104:2017 - Fire stopping and sealing products, penetration seals
- UL-EU-01213-CPR based on EAD 350454-00-1104:2017

PRODUCT INFORMATION

Composition	Graphite	
Packaging	300 ml cartridge	12 cartridges per box
	600 ml foil pack	12 foil packs per box
	Refer to current price list for packaging variations.	
Colour	Anthracite	
Shelf life	18 months from the date of production	
Storage conditions	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging.	

TECHNICAL INFORMATION

Resistance to fire	Refer to 'Approvals / Certificates' or contact Sika Technical Services for additional information.
Service temperature	-15 °C min. / +75 °C max.

APPLICATION INFORMATION

Ambient air temperature	+5 °C min. / +30 °C max.
Substrate temperature	+5 °C min. / +30 °C max., min. +3 °C above dew point temperature

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTATION

- Sika Application Manual: SikaSeal®-623 Fire+
- Sika Fire Stopping Solution Finder for Penetration Seals
- Brochure Sika Fire Protection Solutions

IMPORTANT CONSIDERATIONS

- Do not use SikaSeal®-623 Fire+ as glass sealer, for floor joints, sanitary joints, on natural stone.
- Do not use SikaSeal®-623 Fire+ on bituminous substrates, natural rubber, EPDM rubber or on any building materials which might leach oils, plasticizers or solvents that could degrade the sealant.
- Do not use SikaSeal®-623 Fire+ for joints under water pressure or for permanent water immersion.
- Bare metal in contact with SikaSeal®-623 Fire+ must be protected against corrosion using a suitable primer / protection.
- SikaSeal®-623 Fire+ may only be used for applications and in combination with products it was tested for.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

Substrate preparation

The substrate must be clean, dry, sound and homogeneous, free from oils, grease, dust and loose or friable particles.

SikaSeal®-623 Fire+ adheres without primers and/or activators.

Application

Reference must be made to the relevant Sika Application Manual or contact Sika Technical Services for additional information.

Cleaning of equipment

Clean all tools and application equipment with water immediately after use. Hardened material can only be removed mechanically.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Services AG

Tüffenwies 16
8048 Zürich
Tel: +41 58 436 4040
www.sika.com

PRODUCT DATA SHEET

SikaSeal®-623 Fire+
April 2025, Version 02.0
020517010060000002

SikaSeal-623Fire+-en-(04-2025)-2.pdf

